



ATLANTIC

version 7/08/2019
replaces 25/07/2019

Výrobní postup		všiváný 1/10"	
Typ vlákn		smyčkový	
Materiál vlasu		100% PA 6 BCF	
Metoda barevní		barveno roztokem	
Podklad		AB	
Hmotnost vlasu	ISO 2424	g/m2	1.000 (+/-)
Celková hmotnost	ISO 8543	g/m2	2.150 (+/-)
Výška vlasu	ISO 1766	mm	3,5 (+/-)
Celková výška	ISO 1765	mm	6,5 (+/-)
Počet vpichů	ISO 1763	/m2	182.500 (+/-)
Šíře		cm	400
Třída zátěže	EN 1307	33	komerční vysoká
Třída komfortu	EN 1307	LC 2	
Kolečková židle	EN 985	A	
Schodiště	EN 1963	B	
Hořlavost	EN 13501-1	Cfl-S1	
Elektrostatické vlastnosti	ISO 6356	kV	≤ 2,0
	ISO 10965	Ω	≥ 10¹⁰
Tepelná odolnost	ISO 8302	m2/KW	0,072
Absorpce zvuku	ISO 354	α _w	
	ISO 10140	ΔL _w	24 dB
	ISO 10140	ΔL	(1000 Hz)
Barevná stálost světlo	ISO 105 B02	≥ 6	
Stálost při oděru	ISO 105 X12	≥ 4	
	DIBt Nr.	Z-156.601-1010	



 18 EN 14041 DOP 000576A-002	
TAPIBEL NV Industrielaan 4 B-3900 Pelt Belgium +32 11 80 48 50 sales@tapibel.be www.tapibel.be	
EN 1307 for use as floorcovering in buildings (EN 14041) according to the manufacturer's specification	



TÜV Emission testing

Results comply with emission threshold of

- AgBB - Germany
- Belgian VOC regulation
- BREEAM Exemplary level
- French VOC regulation
- LEED V4 (outside North America)



MAINTENANCE - INSTALLATION

visit our website www.tapibel.be or contact
the sales desk for more detailed information

ALSO AVAILABLE



These technical details are approximate. Complete specification details and associated certificates together with tolerances applying to the above can be provided upon request, if available. We reserve the right to alter specifications without notice. Due to the method of manufacture, perfect pattern/colour matching cannot be guaranteed.
Shading/pile reversal might occur in cut pile carpets, without affecting overall quality and suitability. It is not considered as a manufacturing fault.