



# COBALT SDN

version **draft 18.02.22**  
replaces

Výrobní postup				všivaný 1/10"
Typ vlákn				smyčka
Materiál vlasu				100% PA 6
Metoda barvení				barveno roztokem
Podklad				AB
Hmotnost vlasu	ISO 2424	g/m2	550	(+/-)
Celková hmotnost	ISO 8543	g/m2	1.825	(+/-)
Výška vlasu	ISO 1766	mm	3,0	(+/-)
Celková výška	ISO 1765	mm	5,5	(+/-)
Počet vpichů	ISO 1763	/m2	164.000	(+/-)
Šíře		cm	400	(+/-)
Třída zátěže	EN 1307		33	vysoká komerční
Třída komfortu	EN 1307		LC 1	
Kolečková židle	EN 985		A	
Schodiště	EN 1963		A	
Hořlavost	EN 13501-1		Bfl-S1	
Elektrostatické vlastnosti	ISO 6356	kV	≤ 2,0	
	ISO 10965	Ω	≤ 10 <sup>9</sup>	
Tepelná odolnost	ISO 8302	m2/K/W	0,065	
Absorpce zvuku	ISO 354	α <sub>w</sub>	0,20	
	ISO 10140	ΔL <sub>w</sub>	26 dB	
	ISO 10140	ΔL	44 dB	(1000 Hz)
Barevná stálost světlo	ISO 105 B02		8	
Stálost při oděru	ISO 105 X12		4-5	
Odolnost vůči vodě	ISO 105 E01		5	




<p>19 EN 14041 DOP 000423A-003</p>	
<p>TAPIBEL NV Industrielaan 4 B-3900 Pelt Belgium +32 11 80 48 50 sales@tapibel.be www.tapibel.be</p>	
<p>EN 1307 for use as floorcovering in buildings (EN 14041) according to the manufacturer's specification</p>	



### Kobercové čtverce

k dostání v provedení 50x50 cm a 25x100 cm (100m2)



These technical details are approximate. Complete specification details and associated certificates together with tolerances applying to the above can be provided upon request, if available.

We reserve the right to alter specifications without notice.

Due to the method of manufacture, perfect pattern/colour matching cannot be guaranteed.

Shading/pile reversal might occur in cut pile carpets, without affecting overall quality and suitability. It is not considered as a manufacturing fault.